

X18-154A

Film comprised primarily of Braskem I'm Green PE[®] hexene LLDPE.



Property		ASTM Method	Units	Typical Value
Gauge		D-2103	mils	3.80
Yield		calculated	sq inches/pound	7,921
Basis Weight		calculated	pounds/3000 sq ft	54.5
Haze		D-1003	percent	15
Coefficient of Friction	out-out	D-1894	ratio	
	Film to film in-in	D-1894	ratio	< 0.2
Tensile, Break	MD	D-882	psi	4,100
	TD	D-882	psi	3,600
Elongation, Break	MD	D-882	percent	630
	TD	D-882	percent	870
1% Secant Modulus	MD	D-882	psi	36,000
	TD	D-882	psi	38,000
Dart Drop (26")		D-1709	grams	520

The information presented on this data sheet has been established by company laboratory testing. This information does not imply any warranty by the company of product specifications, tolerances, or functionality in relation to the end use.

